

*Self-adhesive Digital Imaging Media for wide-format inkjet Printing***PRODUCT DESCRIPTION**

FACE MATERIAL : 85 µ white matt, calendered PVC film.  
 ADHESIVE : Permanent, aggressive clear acrylic.  
 LINER : PE Coated Kraft liner 150 gsm .

**TYPICAL USES**

*The product is designed for the production of outdoor sidewalk and parking lot floor graphics. It bonds well to flat or slightly rough, pedestrian traffic surfaces like concrete and asphalt. Almost anywhere you have pedestrian traffic, StreetRap can present your message to customers, clients, visitors and employees: Fairs, Trade Shows, Retail outlets, Convention Centers, Public buildings, Safety messages, Schools, Sport or Entertainment venues.*

**PRINTING**

Solvent based, eco-solvent, mild solvent or latex inkjet printing on wide-format printing equipment.  
 To achieve the best possible print quality, please make sure that the correct ICC profiles or printer settings are used. Profiles can be obtained from our Subsidiaries, Distributors or can be downloaded from <http://www.mactac.eu>  
 Printer & Heater settings and ICC profiles are also downloadable from some of the OEM or software websites.

**PHYSICAL PROPERTIES OF THE UNPRINTED FILM**

	Average values	Test method
<b>Adhesive Data, 23°C</b> Quick Tack on glass Peel 24 hours on glass	46 ± 5 N/25 mm 31 ± 5 N/25 mm	FTM 9 FTM 1
<b>Dimensional stability</b> Shrinkage : 48 hours at 70°C (applied on aluminium)	max 1.0mm	FTM 14
<b>Flammability</b>	Self-extinguishing applied on Alu panels	
<b>Temperature ranges</b> Minimum application temperature : Service temperature range :	+ 10°C - 40°C to + 100°C	

**SHELF LIFE**

2 years when stored at 15 to 25°C and ± 50 % relative humidity (in the original packaging).

**EXPECTED DURABILITY**

The expected vertical outdoor durability of the unprocessed product in Central Europe (Zone 1) is up to:

- 3 months for pedestrian traffic on smooth surfaces if overlaminated with [StreetRap Protect](#), [FloorGrip](#)
- 6 months for pedestrian traffic on smooth surfaces if overlaminated with [StreetLam](#)

This information is based on successful real life experience and artificial aging according to ISO4892-3.

Note : Overlamination of the inkjet printed material delays eventual colour fading that may occur upon time. This colour fading is dependent from the quality of the inkjet inks, the orientation of the printed material, the angle of display and the exact location of exposure on the Globe.

Exposure to severe temperatures, ultra-violet light as well as conditions in Southern European countries, tropical, sub-tropical or desert regions will cause more rapid deterioration. This also applies to polluted areas, high altitude and south facing exposure. No durability warranty is given for horizontal exposure. For more information, please refer to Technical Bulletin 7.5: "Outdoor Durability of combined MACTac print media and laminates".

## **RECOMMENDATIONS**

Always test the combination of JT 5000 products, inks and laminating films prior to commercial use.

### **➤ Printing conditions**

A conditioned pressroom,  $\pm 23^{\circ}\text{C}$  and 50 % R.H.

### **➤ Laminating conditions**

Please ensure the print is perfectly dry. The printed material should be left to dry for at least 48 hours prior to lamination or transport.

Overlamination of the inkjet-printed material is required for slip resistant *StreetRap*.

### **➤ Transportation conditions**

To allow easy transportation, *StreetRap* can be rolled up, with the image on the outside, with a minimum diameter of 15 cm (for example on a 6 inches core).

To avoid exposing the print to any liquid aggressions, prints should be protected by a plastic bag. During the transport or storage of the prints, avoid exposing them to extreme temperature and humidity variations.

## **APPLICATION REQUIREMENTS:**

1° The surface must be absolutely dry, clean and in reasonable good condition.

2° *StreetRap* must be applied in dry weather to a dry surface at temperatures above  $10^{\circ}\text{C}$  on days the temperature is expected to rise to at least  $18^{\circ}\text{C}$ . The weather should remain dry for minimum 24h after application to ensure adhesion build-up on the surface.

Heat helps the adhesive to flow to the rough surface to create a better bond. Do not attempt to apply graphics late in the day when the temperature is expected to cool down.

3° The rougher the surface the less contact the adhesive will have and the less chance your graphic has for success.

4° To clean the surface, use a brush or a stiff bristle broom to remove dirt and dust, sand and gravel or other loose contaminants. Do not use water or cleaners which will cause the surface to become wet.

5° Once aligned, pull back 5cm of the liner to expose the adhesive to align and start the application.

Remove 20cm of liner at a time and using a firm squeegee, short bristle brush or semi-hard roller with firm pressure, forcing the adhesive down into the surface. Make sure to eliminate air bubbles.

6° Bridge graphics over seams if needed but do not force the graphic down into the seam.

7° Once complete go back over all edges with firm pressure to make sure they are all in full contact to the surface.

8° If possible trim sharp corners to a rounded radius to help minimize edge lifting.

9° On rougher surfaces use heat and pressure to conform the graphic to the surface.

10° Do not have multiple layers of overlap on your graphic. This may result in trips, falls and injuries.

## **GENERAL REMARK : factors affecting adhesion**

To ensure application suitability - always test the proposed construction under actual application and end-use conditions before going into full production.

The following factors will adversely affect adhesion of a pressure-sensitive adhesive:

- \* Dusty, dirty, oily or oxidized surfaces

- \* Application below the minimum application temperature or use outside of the recommended service temperature ranges.

### **IMPORTANT NOTICE**

*All MACtac products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects.*

*Published information concerning MACtac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.*

*Because of the variety of uses of MACtac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages.*

*All specifications are subject to change without prior notice.*