



ZHEJIANG GANGLONG NEW MATERIAL CO., LTD.
MAQIAO WARP KNITTING SCIENCE & TECHNOLOGY INDUSTRIAL ZONE
HAINING ZHEJIANG CHINA
TEL: 0086-573-7768983 FAX: 0086-573-7760999

TECHNICAL DATA

ITEM	DATA	UNIT	TEST METHOD
Fabric	High tenacity yarns 100%PES(1000D)		DIN EN ISO2060
Construction	Weaving 20*20	inch	DIN60001
Total weight	510	g/sq.m	DIN53352 BS3424 method5A
Weight of fabric	170	g/sq.m	DIN53352 BS3424 method5B
Weight of pvc coating	340	g/sq.m	DIN53352 BS3424 method5B
Tensile strength	Warp: 2300	N/5cm	DIN53354 BS3424 method6A
	Weft: 1900		
Tearing strength	Warp: 240	N	DIN53356 BS3424 method 7A
	Weft: 200		
Adhesion	80	N/5cm	DIN53357 BS3425 method9B
Suitable temperature	-20 -----+70	°C	DIN 53372 BS3424 method10
Flame retardancy	No, If the client need, we can reach : DIN75200,B1,B2,NFPA701		
Lacquering	No		

The indexes above are on average, so there will be $\pm 5\%$ tolerance of actual indexes.

本公司声明：请客户按照有关规定或行业标准正确选择并使用本公司产品。本公司仅就产品是否符合本页注明的技术数据和性能负责，除此之外，不对产品承担其它任何法律责任。

(本页技术数据均为算术平均值，允许误差 $\pm 5\%$ 。)

Declaration by GLP: Please choose GLP products suitably according to relative provisions or industrial standards. GLP bears the responsibility for the specified technical and performance data on this page only. GLP is not responsible for any other liability. (The technical data on this page is calculated on average, and $\pm 5\%$ tolerance is acceptable.)