

Technical Data Sheet PET-A GEBAU

Technical parametr:	PET - A GEBAU
Density, kg/cm ³	1,33
Coefficient of light transmission, %	90
Charpy Impact (notched), kJ/m ²	Not break
Tensile Strenght, MPa	60
Tensile Module, MPa	2450
Tensile Elongation, %	250

*** Test results are for reference only.

Held at a thickness of 1.5 mm.

Chief technologist Balashov Dmitry