

DirectTex® AKUSTICO® NewLife FR

Fields of application

.01 .02 .03 .04 .05 .06 .07 .08 .12

Specifications

	606252 303 172
	100 % polyester FR (recycling) weave fabrics PVC-free, recyclable
	ca. 155/ 310 cm ca. 61/ 122 inch other widths available on request
	B-s1, d0 DIN EN 13501-1
	ca. 280 g/m ² ca. 8.3 oz/yd ²
	ca. 0.65 mm ca. 650 µm
	rolls 50 m 55 yd
	heat, ultrasonic cut
	Abrasion resistance DIN EN ISO 12947-2 25.000 tours category B according to DIN EN14465
	Rub fastness (dry & wet) DIN EN ISO 105-X12 grade 4 – 5

Printing methods

print	UV	Latex	Dyesub
Inside	•	•	•
Outside	•	•	•

Article shrinkage (50 sec hold up time)

	shrinkage in cross direction	shrinkage in longitudinal direction	recommended fixing temperature
180°C	0,8 %	1,7 %	•
190°C	1,1 %	2,6 %	
200°C	1,5 %	4,0 %	
210°C	1,9 %	5,7 %	

Certifications

OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
09.0.67573 HOHENSTEIN HTTI
Tested for harmful substances.
www.oeko-tex.com/standard100

*



* in testing



DirectTex® AKUSTICO® NewLife FR

.01 .02 .03 .04 .05 .06 .07 .08 .12



Ref.-Nr.: 606252 303 172 | Preview print sample



PONGS Technical Textiles GmbH

Bahnhofstraße 21
07919 Pausa-Mühltröf
Germany

Phone +49 36645 350-0
salestt@pongs.de
www.pongs.com

We reserve the right for technical modifications.
The above mentioned details are non-binding.
A tolerance of $\pm 5\%$ is valid. Effective: 2019/10