

Macal Truck Tarp

PRODUCT DESCRIPTION

Macal Truck Tarp are cast vinyl film coated with specific adhesive designed to give a permanent adhesion on highly plasticized PVC banners or tarpaulins..

Macal Truck Tarpaulin is designed for computer cutting, fast weeding and can be printable in digital print machines.

The serie is available in six popular opaque matt colours. A matt laminating film is available to protect the printed media, a dedicated Technical datasheet is issued - see 'Macal Truck Tarp Laminated'...

Face material:

80 µm, cast vinyl, cadmium free

Adhesive:

Acrylic clear permanent on plasticized PVC only

Liner

Clay coated 140 g/sqm with grey backprinting.

TYPICAL USE

Macal Truck Tarp are designed for exterior marking applications on curtain-side vehicles.

The film shows permanent adhesion on major Tarpaulin manufacturers (Sioen, Dickson, Heytex, Verseidag).

COLOR MATCHING

Customer colour matching service is provided by MACtac. This colour match can be requested from a minimum quantity of 10 rolls (500 lm).

PROCESSING

Especially designed for flatbed and roll to roll signcutting machines. The white colored film is also printable in solvent, Eco-solvent, Latex and UV inkjet printing on wide-format printing equipment.

For further information on the use and applications of Macal Truck Parp, please refer to TB 5.1 "Guidelines on handling, converting and applying Macal Truck Tarp Film."

SHELF LIFE

2 years when stored at 15 to 25°C and \pm 50 % relative humidity (in the original packaging).

APPLICATION METHOD

Macal Truck Tarpaulin can be applied either in wet or dry application methods. Detailed instructions are given in the TB 5.1 "Guidelines on handling, converting and applying Macal Truck Tarp Film." To ensure application suitability, always test the proposed construction under actual application and end-use conditions before going into full production.

PHYSICAL PROPERTIES (TYPICAL VALUES)

Face Material Data, 23°C	Average values	Test method
Tensile strength (N/15mm)	Min 11	ISO 527-3
Elongation at break (%)	Min 150	ISO 527-3
Gloss / Mattity	15	ISO 2813, 85°

Adhesive data, 23°C	Average values	Test method		
Peel 20 minutes on mirror Stainless Steel (N/25mm)	2	FTM 1		
Peel 24 hours on mirror Stainless Steel (N/25mm)	3.5	FTM 1		
Peel 24 hours on Tarpaulin (N/25mm)	15 Film deformation & adhesive transfer	FTM 1		
Dimensional stability				
Shrinkage (48 hours at 70°C applied on aluminium)	Max. 0.2 mm	FTM 14		

Temperature ranges

Minimum application temperature	+ 10°C
Service temperature range of use	-40°C to +60°C

EXPECTED DURABILITY* Central Europe Zone 1

Unprocessed	5 years	ISO 4892-2.	

Note: Exposure to severe temperatures, ultraviolet light, and/or conditions in Southern European countries, tropical, sub-tropical or desert regions will cause more rapid deterioration. This also applies to polluted areas, high altitudes and south-facing exposure. No durability warranty is given for horizontal exposure.

Important notice Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.



Disclaimer and warranty Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com. Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.

